



RIPPLE Construction Products PVT LTD+
 Corp Office: 303 & 404, Royal Arcadia
 SR Nagar, Hyderabad – 500 038
 India

Eurofins Product Testing A/S
 Smedeskovvej 38
 DK-8464 Galten
 Denmark

Tel. +45 70 22 42 76
 Fax +45 70 22 42 75
 voc@eurofins.dk
 www.eurofins.com/product-emissions

Date
 8 October 2014

Your ref.
 -

Our ref.
 G15982E/IB_06

Test Report – LEED 2009 EQ c4.1, SCAQMD rule 1168 (2005)

Sample material

Sample identification	R-Fix
Product type	Construction Adhesive
Product data, according to manufacturer	Density: 1.41 g/ml at 23 °C ** Water content: 0 g/l** Exempt compounds***.
Date received	20 June 2012
Analytical period	July 2012

Methods applied

Method	Principle	Parameter	Detection limit	Uncertainty
LEED 2009 EQ c4.1 ASTM D 2369 - 10	Gravimetric	Total Volatiles, SCAQMD rule 304	1 g/l	10 %

Volatile content of the sample was determined gravimetrically by heating up to 110 °C during 60 minutes. The result is the average of double testing. The result was calculated as:

$$([g \text{ all volatiles}] - [g \text{ water}] - [g \text{ exempt compounds}]) / ([l \text{ material}] - [l \text{ water}] - [l \text{ exempt compounds}])$$

U_m (%): The expanded uncertainty U_m is equal to 2 x RSD%, see also www.eurofins.dk, keyword: Uncertainty.

Analytical results

	Solid content, % mass	Water content, % mass	Exempt compounds, % mass	VOC less wa- ter less ex- empt com- pounds, g/l	VOC limit g/l
R-Fix	97.4	0**	0***	37	70*

* VOC limit for “Multipurpose Construction Adhesives”

** Given by the client

*** No information about exempt compounds. Set to zero.

Eurofins Product Testing A/S

Morten Sielemann

Analytical Chemist